

Dribond Rapid Set 45

NON-SLUMP, FAST SET, PATCHING AND REPAIR COMPOUND

PACKAGING



MIXING




APPLICATION



USES



FLOOR



WALL

SUBSTRATES

CONCRETE
BRICK
BLOCK
RENDER WALLS

DESCRIPTION

A fast setting, non-slump, cement patching and repair compound.

FEATURES

- Develops high strength
- Good bond to masonry surfaces
- Low shrinkage
- Sets in 1 hour.

USES

A fast set patching repair compound for concrete and masonry surfaces (cement render brick and block). Typical applications are; repairing concrete stairs; patching holes in floors and walls and for forming falls from featheredge to 45mm and for forming coves. Patching and filling different floor levels and repairing around windows, doors, pipes etc.

PERFORMANCE DATA

• Compression Strength – BS4551. (Mpa)	1 Day	28 Days
• Tensile Strength – BS4551. (Mpa)	18.0	31.0
• Hardness – Brinnell. (Mpa)	4.0	6.0
	54	78

COVERAGE (approximate)

1.5kg Rapid Set 45 will cover 1m² at 1mm thickness.

SPECIFICATION

The repair compound will be a non-slump, fast setting polymer modified cement system with a compressive strength of 31 Mpa, such as Rapid Set 45, manufactured by Construction Chemicals and shall be applied in accordance with the manufacturers application instructions.

SURFACE PREPARATION

Surfaces must be firm and clean, free from dust, waxes, oil, grease, paint, excessive water and other contaminants. Smooth and contaminated surfaces must be mechanically roughened, washed thoroughly and allowed to dry. Dense surfaces should be primed with Bonding Additive Slurry.

MIXING

Place 4.5 litres of water in a mixing container and add the 20kg of powder while stirring continuously. Mix thoroughly until a lump free, slump free mixture is obtained. Avoid using excessive water. Mix and place in 10-15 minutes at 20°C.

APPLICATION

When exceeding thicknesses of 20mm add 1/3 sharp washed sand up to 45mm. When filling holes and

cracks, leave the patch slightly proud and trim off the excess after 15 minutes and finish with a wet trowel.

SET TIME

Approximately 1 hour, depending on temperature, humidity and surface porosity.

CURING

Curing is not normally required but in direct sunlight and hot dry conditions, moist cure for 24 hours.

SHELF LIFE

1 year.

PRECAUTION

Contains cement which contains silica and is alkaline - gloves should be used, avoid inhaling dust and avoid contact with eyes.

1ADELAIDE
1BRISBANE
1MELBOURNE
1PERTH
1SYDNEY
1AUCKLAND
1KUALA LUMPUR

"The information contained in this technical publication is based on our current knowledge and experience and is provided as a guide only. In view of the many factors that may affect application it is the users sole responsibility to ensure suitability for a specific purpose."