



"From time of pour to finished floor...we've got you covered"

PRODUCT DATA SHEET

STONE SEAL

Description	Stone Seal is a high grade, tough and durable penetrating sealer that has been formulated to give protection against sunlight, traffic, oil and dirt.																		
Features	<ul style="list-style-type: none"> • UV resistant • Easy to apply • Hard durable coating • Non yellowing • Anti slip properties • Excellent scuff resistance 																		
Typical Uses	Stone Seal is designed for the protection and enhancement of concrete, stone, terrazzo, marble, ceramic tiles (no glazed), terracotta, concrete bricks and other absorbent surfaces.																		
Application Data	<table border="0" style="width: 100%;"> <tr> <td style="width: 50%;">Gloss:</td> <td>Matt</td> </tr> <tr> <td>Colour:</td> <td>Clear</td> </tr> <tr> <td>Shelf Life @ 25°C:</td> <td>6-12 months</td> </tr> <tr> <td>Thinning:</td> <td>Xylene</td> </tr> <tr> <td>Clean Up:</td> <td>Xylene</td> </tr> <tr> <td>Spread Rate:</td> <td>4m² – Porous material 10-12m² – Smooth material This will vary depending on surface absorption and method of application.</td> </tr> <tr> <td>Dry Times:</td> <td>Dust Free: 20-30 minutes Touch Dry: 1 hour Hard Dry: 12-24 hours</td> </tr> <tr> <td>Application:</td> <td>May be applied by brush, roller, conventional spray, or broom. To achieve maximum build do not thin. First coat should be thinned 10-20% with Xylene thinners depending on how porous the concrete is and the application equipment used.</td> </tr> <tr> <td>Container Sizes:</td> <td>20 litre</td> </tr> </table>	Gloss:	Matt	Colour:	Clear	Shelf Life @ 25°C:	6-12 months	Thinning:	Xylene	Clean Up:	Xylene	Spread Rate:	4m ² – Porous material 10-12m ² – Smooth material This will vary depending on surface absorption and method of application.	Dry Times:	Dust Free: 20-30 minutes Touch Dry: 1 hour Hard Dry: 12-24 hours	Application:	May be applied by brush, roller, conventional spray, or broom. To achieve maximum build do not thin. First coat should be thinned 10-20% with Xylene thinners depending on how porous the concrete is and the application equipment used.	Container Sizes:	20 litre
Gloss:	Matt																		
Colour:	Clear																		
Shelf Life @ 25°C:	6-12 months																		
Thinning:	Xylene																		
Clean Up:	Xylene																		
Spread Rate:	4m ² – Porous material 10-12m ² – Smooth material This will vary depending on surface absorption and method of application.																		
Dry Times:	Dust Free: 20-30 minutes Touch Dry: 1 hour Hard Dry: 12-24 hours																		
Application:	May be applied by brush, roller, conventional spray, or broom. To achieve maximum build do not thin. First coat should be thinned 10-20% with Xylene thinners depending on how porous the concrete is and the application equipment used.																		
Container Sizes:	20 litre																		

Application Summary	Always apply to a small area first (approx. 1m ²) and leave to dry to establish both suitability and coverage rate. Coverage will vary depending on porosity of the surface and will range between 4m ² per litre on exposed aggregate and porous surface, up to 12m ² on very smooth surfaces. New concrete surfaces should be allowed to cure 21-28 days before sealing. Ensure the concrete surface is clean and dry before applying sealer. Application of sealer over contaminants such as moisture and dirt may reduce adhesion and cause discolouration. Two coats of sealer should be applied to the surface. Spread the sealer over the surface in an even way so that the concrete is completely covered with a thin layer of sealer. If 'pooling' occurs, immediately spread the sealer over the surrounding area. Do not apply a second coat until the first coat has dried. For best results leave overnight and then apply an undiluted coat of sealer in the same manner described above.
Precautions	Contains flammable solvents. Keep away from heat and flame. Provide adequate ventilation and wear protective clothing. Material Safety Data Sheet available on request.
Classification	UN 1263 DG CLASS 3 PKG II HAZCHEM 3 [Y]E