

# Non-Shrink Grout

## Packaging





## Mixing



## Application



## Uses



## Substrates

Concrete  
Brick, Block  
Cement render

## Class A expanding grout

### Description

A premixed, non-shrink class A cement grout. An expanding non-ferrous grout consisting of a dry, premixed blend of Portland cement and graded, siliceous aggregate with set regulating and reactive chemical agents.

**Contains no calcium chloride.**

### Uses

- Underpinning and brickwork repairs
- Grouting of machine bases, column bases (steel and precast concrete) anchor bolts and similar grouting applications
- Patching holes in masonry surfaces

### Features

- Controlled expansions, ensuring positive surface contact
- No corrosive effect caused by metallic residue
- No rusting or staining on exposed edges
- Premixed, addition of water only needed

### Performance Data

#### Strength

The following strength development pattern is typical for a dry pack grout mix.

**Non-Shrink Grout:** Water ratio - 50 parts by weight to 7 parts by weight.

#### Compression Strength

(50.8mm cubes restrained) (ASTM C109)  
33MPa (3 days)  
45MPa (7 days)  
60MPa (28 days)

#### Expansion

Free expansion - approximately 2.9%.  
Expansion complete in 1.5 hours.

#### Setting time

**Non-Shrink Grout** will develop initial set in approximately 1.5 hours @ 22°C. Lower temperatures will increase set times.

### Coverage (Approximate)

For each cubic metre of grout required allow approximately 100 x 20kg bags.

### Specification

The **Non-Shrink Grout** will be a non-metallic cement grout and shall have a minimum compression strength of 60MPa such as **Non-Shrink Grout** manufactured by **Construction Chemicals** and shall be applied in accordance with the manufacturers instructions.

### Surface Preparation

All surface laitance and unsound concrete must be chipped away so that a reasonably rough, but strong sound surface is provided. All surfaces must be free from oil, grease and dust, this particularly applies to the underside of bed plates, bolts, pipes or other materials which may have surface contact with the grout. After cleaning, saturate the concrete surfaces with clean water for approximately 6 hours prior to applying **Non-Shrink Grout**. Ensure that no freestanding water is present on surfaces of foundations or in bolt holes before applying **Non-Shrink Grout**.

### Mixing

Add clean water to **Non-Shrink Grout** (premixed) in ratio recommended for grout consistency required. Use as little water as is required for ease of placement.

#### Flowable Grout

Up to 4 litres water to 20kg **Non-Shrink Grout**.

#### Plastic Mortar Mix

Approximately 3 litres water to 20kg

#### Non-Shrink Grout.

#### Dry-Pack Mortar Mix

Approximately 2 litres water to 20kg

#### Non-Shrink Grout.

Job conditions, including temperatures, may require adjustments as may be essential for practical purposes. Small trial batches to ascertain the best working consistency for the operation are recommended.

Use mechanical mortar mixes, preferably of the paddle or revolving drum type. Hand mixing rarely achieves the desired results. Allow approximately 5 minutes mixing. Thorough mixing is essential for achieving maximum results.

**Non-Shrink Grout** should be placed within 1/2 hour of mixing. During that time, keep material in mixer well agitated. After 1/2 hour discard any grout mix that shows signs of stiffening.

### Application

#### Flowable Non-Shrink Grout

May be used with low pressure cement grout equipment or may be hand rodded into restrained sections. High points must be adequately vented to allow entrapped air to escape.

**Plastic Non-Shrink Grout**

May be rodded into place or trowelled where freedom of movement permits. Consistency can range from a thick paste to a smooth plastic mix.

**Dry-Pack Non-Shrink Grout**

Must be firmly presses or rammed into place. Use metal or hardwood tamping tools and suitable trowel equipment. Consistency should allow forming into firm hard ball without cracking.

**Note: Use clean equipment at all times. Wash mixers, pressure equipment and hand tools with clean water promptly after use.**

**Storage**

Store in dry, cool conditions.

**Shelf Life**

1 year



**Adelaide** Phone (08) 8243 7888

**Darwin** Phone (08) 8947 1811

**Perth** Phone (08) 9356 9999

**Auckland** Phone (09) 273 5444

**Brisbane** Phone (07) 3271 2944

**Melbourne** Phone (03) 9761 4711

**Sydney** Phone (02) 9756 3533

**Kuala Lumpur** Phone (603) 5122 2522

[www.constructionchemicals.com.au](http://www.constructionchemicals.com.au)

The information contained in this technical publication is based on our current knowledge and experience and is provided as a guide only. In view of the many factors that may affect application it is the user's sole responsibility to ensure suitability for a specific purpose.